

glove@n Vigor LC

Nitrile Exam Gloves Powder Free, Long Cuff

Longer in cuff length, GloveOn[®] Vigor LC is designed for its robustness and hardiness to get the tough jobs done. The vibrant choice of orange highlights Vigor LC's uniqueness and suitability for industrial and hospitality markets.



Physical Dimensions				
Length (mm)	290 <u>+</u> 10			
Palm Thickness (Centre of Palm) (mm)	0.13 ± 0.02			
Finger Thickness (13mm \pm 3mm from tip) (mm)	0.17 ± 0.02			
Physical Properties	Before Ageing	After Ageing		
Tensile Strength (MPa)	≥ 18	≥ 16		
Elongation (%)	≥ 500	≥ 400		
Performance Requirements	Inspection Level	AQL		
Performance Requirements Watertightness	Inspection Level G1	AQL 1.5		
Watertightness	G1	1.5		
Watertightness Physical Dimensions	G1 S2	1.5 4.0		
Watertightness Physical Dimensions Physical Properties	G1 52 52	1.5 4.0 4.0		

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978 - Test Report PN 118903 & PN 169211A)	Minimum Breakthrough Detection Time (minutes
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	45.4 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Mycophenolate Mofetil, 6.0mg/ml (6,000 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Tacrolimus, 5.0mg/ml (5,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	30.9 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes
WARNING: Carmustine and Thiotena, at the tested concentration, degraded Vigor I C nitrile glove	at 45.4 minutes and 30.9 minutes respect

REORDER CODE

VGR611SS	SMALL
VGR611MM	MEDIUM
VGR611LL	LARGE
VGR611XL	X-LARGE

FEATURES

- Fingertip textured
 Powder free
- Not made with natural rubber latex
- Chemo drugs tested
 Lab chemical tested
- Ambidextrous Long cuff Orange colour

PACKAGING

100 gloves per box for S to XL 10 boxes per carton

REGULATORY COMPLIANCE

ARTG 407779, FDA 510(k), REACH, MDR 2017/745, EC 1935/2004, RoHS Directive 2011/65/EU, EU 10/2011, EU 2016/425

STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124, ASTM D6978, EN 16523-1, EN ISO 21420, EN ISO 374 part 1 (Type B), 2, 4 & 5, EN 1186, EN 455 part 1, 2, 3 & 4, EN 13130, EN 421 (excluding Clause 4.3), ISO 11193-1, ISO 10993 part 5 & 10, CEN/TS 14234, HACCP International Certified

MANUFACTURING ACCREDITATIONS ISO 9001, ISO 13485, EN ISO 13485

/ARNING: Carmustine and Thiotepa, at the tested concentration, degraded Vigor LC nitrile glove at 45.4 minutes and 30.9 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Chemical	EN 16523-1 Permeation Level	EN ISO 374-4 Mean Degradation (%)		Measured breakthrough time (minutes) Permeation performance level	>10	>30	>60	>120	>240	>480
J n-Heptane K 40% Sodium Hydroxide P 30% Hydrogen Peroxide T 37% Formaldehyde	3 6 2 6	33.9 -19.9 34.5 -11.0	P	Product disclaimer - https://munglobal.com	/product	-disclaim	er/	4		0

A brand by

Mun Australia Toll free: 1800 456 837 munglobal.com.au



