



gloveon

Paladin

Nitrile Exam Gloves Powder Free, Long Cuff

GloveOn® Paladin is the 5ml thick long cuff glove ideal for jobs that demand extra tensile strength, and added protection. As such, GloveOn® Paladin is used extensively in medical centres, laboratories, manufacturing and by the shining knights of the emergency and rescue services.



GloveOn® Paladin		
Length (mm)	≥ 280	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.10 ± 0.02	
Finger (13mm ± 3mm from tip)	0.13 ± 0.02	
Cuff (25mm from cuff edge)	0.08 ± 0.02	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

REORDER CODE

NTR36XS	X-SMALL
NTR36SS	SMALL
NTR36MM	MEDIUM
NTR36LL	LARGE
NTR36XL	X-LARGE
NTR362XL	XX-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Long cuff
- Cobalt blue colour

PACKAGING

100 gloves per box
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 164563, MDD 93/42/EEC,
REACH, ROHS Directive 2002/95/EC,
EU 2016/425

STANDARDS

AS/NZS 4011-1, ASTM D6319,
ASTM D5151, ASTM D6124, ASTM D6978,
EN ISO 374-1 (Type B), EN 16523-1,
EN 374 part 2, 4 & 5, EN 455 part 1, 2, 3 & 4,
EN 1186, EN 13130, CEN/TS 14234,
ISO 10993 part 5 & 10, HACCP Certified

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration
(Tested for Resistance to Permeation by Chemotherapy
Drugs as per ASTM D6978-05-Test Report PN 101115B)

Minimum Breakthrough
Detection Time (minutes)

Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	30.1 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytosan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	57 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Paladin nitrile glove at 30.1 minutes and 57 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

A brand by



Mun Australia
Toll free: 1800 456 837
mungallobal.com.au



Proud Supporter of
Birthing Kit Foundation (Australia)



Protection Always On

MKG2019-059