



Nitrile Exam Gloves Powder Free, Standard Cuff

GloveOn® Celeste is a popular choice from our nitrile exam glove range. With high tensile strength and resistance to chemicals, GloveOn Celeste's superior tactility commends it to delicate procedures













	GloveOn® Celeste	
Length (mm)		
	≥ 230	
Thickness Measurements (mm)		
Palm (centre of Palm)	0.07 ± 0.02	
Finger (13mm ± 3mm from tip)	0.09 ± 0.02	
Physical Properties	Before Ageing	After Ageing
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Inspection Levels & AQL	Inspection Level	AQL
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Tensile Strength	S2	4.0
Visual Inspection (Major)	\$4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978-05-Test Report PN 145460)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	16.2 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	28.4 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Celeste nitrile glove at 16.2 minutes and 28.4 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Mun Australia

Toll free: 1800 456 837

munglobal.com.au

REORDER CODE

NTR58XS X-SMALL NTR58SS SMALL NTR58MM MEDIUM NTR58LL LARGE NTR58XL X-LARGE

FEATURES

- Fingertip textured
- Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested
- Ambidextrous
- Standard cuff
- Violet blue colour

PACKAGING

200 gloves per box for XS to L 180 gloves per box for XL 10 boxes per carton

REGULATORY COMPLIANCE

ARTG 164563, FDA 510(k), MDD 93/42/EEC, REACH, ROHS Directive 2002/95/EC, EU 10/2011, EC 1935/2004, EU 2016/425

STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124, ASTM D6978, EN ISO 374-1 (Type B), EN 374 part 2, 4 & 5, EN 16523-1, EN 420, EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130, CEN/TS 14234, ISO 10993 part 5 & 10, HACCP Certified

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485





Birthing Kit Foundation Australia

Proud Supporter of Birthing Kit Foundation (Australia)

